



CERULEAN NR 11 is a Natural Rubber Compound and is Sulphur curable.

Material Data

S.No	Description	ASTM Test Method	Unit	Spec
1.	Hardness	D 2240	Shore A	60±5
2.	Tensile Strength	D 412	MPa	10 (Min)
3.	Elongation @ break	D 412	%	350 (Min)
4.	Compression Set 22hrs@70°C	D 395 Method B	%	25 (Max)

Note: This information is to the best of our knowledge, accurate and reliable and it does not necessarily indicate the end product performance. Hence, it is the customer's responsibility to evaluate the parts prior to use, especially in applications where the failure may result in injury and or damage.

Features & Benefits

- Excellent Abrasion Resistance
- Excellent Mechanical Properties
- Good Wear & Tear Properties
- Operating temperatures from -40°C to +70°C

Applications

- Refrigeration Seals
- Pumps
- Cable wires

Product Range

- Grommets
- Anti Vibration Mounts
- Rubber to Metal Bonded Parts
- Custom Molded parts

