



VERTEX F01 ED is an FFKM 90 Sh-A compound specifically developed for Explosive Decompression Resistance.

Material Data

S.No	Description	ASTM Test Method	Unit	Spec
1.	Hardness	D 2240	Shore A	90±5
2.	Density	D 792	gm/cc	1.95±0.05
3.	Tensile Strength	D 412	MPa	16 (Min)
4.	Elongation @ break	D 412	%	80 (Min)
5.	Compression Set 24hrs@200°C	D 395	%	30 (Max)

The material has outstanding chemical resistance to aggressive media such as hot organic and inorganic acids, caustics, amines (especially hot amines, i.e., at temperature higher than +70 °C), ketones, aldehydes, esters, ethers, alcohols, fuels, solvents, sour gases, hydrocarbons, steam, hot water, ethylene and propylene oxide and mixed process streams. Do not use any "VERTEX F" Series grades with molten alkali metals.

Chemical Resistance Data

Fluid	Volume swelling	Fluid	Volume swelling	Fluid	Volume swelling
Inorganic acids	<10%	Water/Steam	<10%	Alcohols	<10%
Organic acids	<10%	Ketones	<10%	Hydrocarbons	<10%
Alkalis	<10%	Esters	<10%	Sour gas	<10%
Amines (RT)	<10%	Ethers	<10%	Lubricants	<10%
Hot amines (> 70 °C)	<10%	Aldehydes	<10%	Fluorinated fluids	30-50%

Note: This information is to the best of our knowledge accurate and reliable and it does not necessarily indicate the end product performance. Hence, it is the customer's responsibility to evaluate the parts prior to use, especially in applications where the failure may result in injury and or damage.

Features & Benefits

Lower volumetric swell

Higher resistance to wide range of fluids under pressure

Very good chemical compatibility

Unrivalled ED and Chemical resistance

Operating temperatures from -10°C to +230°C

Applications

Valves

Pumps

Mechanical seals

Compressors reactors

Product Range

O rings

Gaskets

Diaphragms

Pump housing

